

# BALACRON

## COVERS

### Product datasheet

Collection : Atelier  
Design: : Emu

Composition		Dimensions	Test method
Total Weight	250 ± 10	gsm	ISO 2286-2
Weight paper	90 ± 3	gsm	
Weight coating	160	gsm	
Total Thickness*	0,33 ± 0,03	mm	ISO 534
Thickness coating	0,21	mm	
Thickness paper	0,12	mm	
Type of coating	PVC with waterbased inks and topcoat		
Type of paper	Mechanical base paper		

\* Depends on grain.

Properties		Dimensions	Test method
<b>Tensile strength</b>			
MD	> = 4,0	daN/15 mm	ISO 1924-2
CD	> = 1,6	daN/15 mm	
<b>Elongation at break</b>			
MD	> = 1,0	%	
CD	> = 2,4	%	
<b>Tear strength</b>			
MD	> = 1400	mN	ISO 1974
CD	> = 1400	mN	
<b>Stiffness L&amp;W</b>			
(Angle 20° Length: 15 mm)			
MD	105 ± 30	mN	ISO 2493
CD	55 ± 20	mN	
<b>Folding resistance</b>			
MD	1350 ± 450	mg	BN meth. 1320
CD	1050 ± 250	mg	
<b>Foil blocking properties</b>			
Kurz Luxor/Alufin AF/AS	Moderate		
Kurz Colorit V	Moderate		
<b>Safety/Ecological</b>			
According to EU regulation 1907/2006EC (REACH) "Emu" Paper Backed vinyl covermaterial is defined as article. This article is not considered to be a hazardous product nor as mixture of dangerous substances. The article contains no substance included on the candidate list according to article 59 (1,10) of regulation (EC) No 1907/2006 ("REACH") in a concentration above the threshold level of 0,1% weight by weight.			
Standard measurement	(L) 100 meter X (W) 106 cm		
Certifications	FSC® certified: FSC-C141806, Non Phthalate		
Last revised productsheet	30-11-16		

**Balacron international BV**  
Rokerijweg 5  
1271 AH Huizen  
The Netherlands  
Tel +31 35 524 84 25  
Mail info@balacron.com  
Web www.balacron.com

